

Project:

Order No: Premio EPS80 Carbon Compression test

Tester: Thümler GmbH-Z5


Part No: P80Carbon/2020_09_16

Method: MSZ EN 826

Customer: Premio Hungária

Execution date: 2020. 09. 16. 9:51:07

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P80Carbon/2020_09_16(2)	86,47	9,99
P80Carbon/2020_09_16(4)	85,82	9,99
P80Carbon/2020_09_16(5)	86,64	10,00
P80Carbon/2020_09_16(7)	85,41	9,99
P80Carbon/2020_09_16(8)	85,71	10,00
Max.	86,64	10,00
Min.	85,41	9,99
Mean	86,01	9,99