

Project:

Order No: Premio EPS100 Carbon Compression test

Tester: Thümler GmbH-Z5


Part No: P100Carbon/2020_11_17

Method: MSZ EN 826

Customer: Premio Hungária

Execution date: 2020. 11. 17. 10:41:31

Chart:



Results:

Nom	Stress [kPa] ,max.	Displacement [mm] ,max.
P100Carbon/2020_11_17(1)	108,49	9,99
P100Carbon/2020_11_17(2)	110,76	9,99
P100Carbon/2020_11_17(6)	107,91	10,00
P100Carbon/2020_11_17(8)	109,59	10,00
Max.	110,76	10,00
Min.	107,91	9,99
Mean	109,19	9,99